

Shrinkage and Absorbtion: Standard Clays

Clay	Cone	Shrinkage	Absorbtion	Clay	Cone	Shrinkage	Absorbtion
103	06	9.00%	12.00%	257	8	13.00%	1.00%
104	06	6.00%	13.20%	257	10	15.00%	0.65%
105	06	6.00%	15.50%	266	4	11.50%	2.40%
112	6	12.50%	2.50%	266	6	13.00%	1.40%
130	7	10.00%	0.75%	306	4	11.00%	4.00%
130	9	12.00%	0.50%	306	10	13.00%	1.00%
153	4	11.00%	6.00%	308	4	12.00%	2.50%
153	10	13.00%	2.00%	308	8	13.00%	1.00%
181	6	13.00%	2.80%	365	6	13.50%	0.60%
182	4	10.00%	6.00%	380	6	7.00%	varies
182	8	11.00%	3.00%	380	10	7.00%	varies
213	6	12.00%	1.70%	420GN	2	7.00%	8.00%
225	6	12.50%	2.50%	420GN	6	8.00%	1.50%
239	04	8.00%	17.00%	470	10		
239	6	13.00%	4.50%	553	6	12.00%	2.70%

Shrinkage and Absorbtion: Highwater Clays

Clay	Cone	Shrinkage	Absorbtion	Clay	Cone	Shrinkage	Absorbtion
Phoenix	6	11.00%	3.90%	Orangestone	6	10.00%	4.80%
Phoenix	10	12.00%	1.00%	Orangestone	10	11.00%	1.30%
Red Rock	6	10.00%	1.00%	Trina Buff	6	12.00%	1.00%
Loafers Glory	6	12.00%	3.90%	Trina Buff	10	11.00%	1.00%
Loafers Glory	10	12.50%	1.00%	Helios	6	11.00%	1.00%
Little Loafers	5	11.00%	3.40%	Helios	10	13.00%	1.00%
Little Loafers	6	11.00%	1.90%				

Shrinkage and Absorbtion: Laguna

Clay	Cone	Shrinkage	Absorbtion	Clay	Cone	Shrinkage	Absorbtion
B-mix 10	10	13.00%	1.00%	Laguna 50	6	12.00%	2.93%
Dark Brown	10	12.00%	0.90%	Soldate 60	04	approx 8%	approx 13%
Miller 10	06	8.00%	11.50%	Soldate 60	6	approx 12%	approx 4%
Miller 20	06	8.50%	11.00%	Soldate 60	10	13.50%	1.75%
Miller 20G	06	8.00%	11.50%				